

DuPont™ Kalrez®

Perfluoroelastomer Parts

Physical Properties and Product Comparisons

Technical Information—Rev. 11, September 2012

DuPont™ Kalrez® perfluoroelastomer parts are available in a number of different compounds that are formulated to optimize properties to give the best possible performance in various applications. Modification of the finished properties is achieved by use of fillers and other additives.

Table 1 summarizes the basic physical properties of the most commonly used Kalrez® products for the chemical and hydrocarbon processing industries. Descriptions of the key attributes for each product and their general areas of application follow.

Table 1. Typical Physical Properties¹

DuPont™ Kalrez® Products	Standard			Specialty				
	6375	7075	4079	6380	7090	0090	0040	1050LF
Maximum Application Temp ² , °C	275	327	316	225	325	250	220	288
°F	527	620	600	437	617	482	428	550
Durometer Hardness, Shore A ³ , points ±5	75	75	75	80	90	95	70	82
100% Modulus ⁴ , MPa	7.24	7.58	7.24	6.89	(50% Modulus) 15.51	(50% Modulus) 14.20	6.61	12.40
psi	1,050	1,100	1,050	1,000	2,250	2,060	960	1,800
Tensile Strength at Break ⁴ , MPa	15.16	17.91	16.88	15.86	22.75	19.51	13.72	18.60
psi	2,200	2,600	2,450	2,300	3,300	2,830	1,990	2,700
Elongation at Break ⁴ , %	160	160	150	160	75	80	180	125
Compression Set ⁵ , % 70 hr at 204 °C (400 °F)	25	12	25	38	12	40	38	35
Tr10 ⁶ , °C	−3	−4	−2	−5	−5	−7	−17	−4
°F	26.6	24.8	28.4	23.0	23.0	19.4	1.4	24.8

¹ Not to be used for specifications

² DuPont proprietary method; performance will vary with seal design and application specifics

³ ASTM D2240

⁴ ASTM D412, 500 mm/min (20 in/min)

⁵ ASTM D395 – Method B, pellets

⁶ ASTM 1329



The miracles of science™

Standard Products

DuPont™ Kalrez® Spectrum™ 6375 is a carbon black-filled product for general use in O-rings, seals, diaphragms and other parts specifically for the chemical process industry. This product has excellent broad chemical resistance, good mechanical properties, and outstanding hot-air aging properties. Kalrez® Spectrum™ 6375 is well suited for use in mixed process streams because of its excellent resistance to acids, bases, and amines. It is also recommended for use in hot water, steam, pure ethylene oxide and propylene oxide.

DuPont™ Kalrez® Spectrum™ 7075 has enhanced physical properties including very low compression set and improved seal force retention. It is a carbon black-filled product utilizing proprietary cure chemistry. Its mechanical properties are designed for improved sealing performance in both high temperature environments and temperature cycling situations. Kalrez® Spectrum™ 7075 O-rings have a glossy finish. This product was specifically developed for the chemical and hydrocarbon industries to provide improved chemical and thermal resistance better than the industry standard set by Kalrez® 4079.

DuPont™ Kalrez® 4079 is a low compression set product for general-purpose use in O-rings, diaphragms, seals, and other parts used in the process and aircraft industries. It is a carbon black-filled product with excellent chemical resistance, good mechanical properties, and outstanding hot air aging properties. It exhibits low swell in organic and inorganic acids and has good response to temperature cycling effects. This product is not recommended for use in hot water/steam applications or in contact with certain hot aliphatic amines, ethylene oxide, or propylene oxide.

Specialty Products

Note: Before ordering Kalrez® parts in specialty products, please consult with DuPont or its authorized distributor technical staff to determine properties needed for the application. Specialty products are generally not held in inventory.

DuPont™ Kalrez® Spectrum™ 6380 is a non-black product specifically developed for chemical processes involving hot, aggressive amines. It has also been successfully used in applications involving highly oxidizing chemicals. In addition, it has excellent overall chemical resistance. This cream colored product is easily identifiable when selecting an O-ring material for harsh chemical plant services.

DuPont™ Kalrez® Spectrum™ 7090 is a product for uses requiring higher hardness/higher modulus than more typical applications. Kalrez® Spectrum™ 7090 perfluoroelastomer parts are well suited for both static and dynamic applications as well as specific sealing applications requiring extrusion resistance at high temperatures. These specialty black parts have excellent thermal and mechanical properties, including excellent compression set and seal force retention, resistance to temperature cycling effects, and rapid gas decompression (RGD). Short excursions to higher temperatures may also be possible.

DuPont™ Kalrez® 0090 is a black product with broad chemical resistance combined with high modulus and high hardness. Kalrez® 0090 parts have outstanding resistance to extrusion and rapid gas decompression (RGD). This product has been independently tested and certified by the Materials Engineering Research Laboratory (MERL – UK) to meet NORSOK-M-710 Rev 2 requirements.

DuPont™ Kalrez® Spectrum™ 0040 is a black product specifically designed for low temperature environments where significant chemical resistance is required. Kalrez® Spectrum™ 0040 parts maintain elasticity and seal force at temperatures unattainable by other perfluoroelastomers.

DuPont™ Kalrez® 1050LF is a carbon black-filled product for O-rings, seals, and other parts used in chemical process industries. It has good hot water/steam, and excellent amine resistance. Kalrez® 1050LF is not recommended for use in organic acids, or inorganic acids at high temperatures.

Other Properties

Other properties, such as coefficients of friction, thermal conductivity, electrical and permeability may be of interest for specific applications. For more detailed information, please refer to the DuPont™ Kalrez® Application Guide available for download at <http://www.dupontelastomers.com/kag>.

Product Safety

Highly toxic products can be generated when Kalrez® parts are exposed to fire or temperatures in excess of 400 °C so respiratory equipment should be used if ventilation is inadequate. Kalrez® parts are incompatible and should not be exposed to alkali metals or interhalogen compounds. Please consult "Guide For Safety In Handling Kalrez® Perfluoroelastomer Parts" (KZE-A10301) for additional information.

Visit us at kalrez.dupont.com or vespel.dupont.com

Contact DuPont at the following regional locations:

North America

800-222-8377

Latin America

+0800 17 17 15

Europe, Middle East, Africa

+41 22 717 51 11

Greater China

+86-400-8851-888

ASEAN

+65-6586-3688

Japan

+81-3-5521-8484

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer service representative and read Medical Caution Statement H-50103-3.

Copyright © 2012 DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™, Kalrez®, Spectrum™, and Vespel® are trademarks or registered trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

(04/08) Reference No. KZE-H68254-00-K0912



The miracles of science™